

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
23 August 2001 (23.08.2001)

PCT

(10) International Publication Number
WO 01/60905 A1

(51) International Patent Classification⁷: C08L 23/02,
23/16, C08J 9/00 // (C08L 23/16, 23:10, 27:18, 33:06)

(74) Agent: SKINNER, William, A.; Advanced Elastomer
Systems, L.P., 388 South Main Street, Akron, OH
44311-1059 (US).

(21) International Application Number: PCT/US01/04924

(22) International Filing Date: 15 February 2001 (15.02.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/182,852 16 February 2000 (16.02.2000) US

(71) Applicant (for all designated States except US): AD-
VANCED ELASTOMER SYSTEMS, L.P. [US/US];
388 South Main Street, Akron, OH 44311-1059 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ,
DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR,
HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR,
LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ,
NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM,
TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BF, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF,
CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).


Published:

- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(72) Inventors; and

(75) Inventors/Applicants (for US only): SAHNOUNE, Ab-
delhadi [DZ/US]; 402 Misty Lane, Akron, OH 44333 (US).
FINERMAN, Terry, M. [US/US]; 1784 Kemery Road,
Akron, OH 44333 (US). JACOB, Sunny [IN/US]; 1915
Burlington Road, Akron, OH 44313 (US). HAM, Sydney
[US/US]; 3680 West Pleasant Home Road, Burbank, OH
44214 (US).



WO 01/60905 A1

(54) Title: THERMOPLASTIC ELASTOMERS HAVING ENHANCED FOAMING AND PHYSICAL PROPERTIES

(57) Abstract: An olefinic thermoplastic elastomer composition which includes an acrylic-modified polytetrafluoroethylene. When foamed, such compositions produce a very soft foam with improved processing properties and physical characteristics. A process of foaming and foamed articles are also disclosed.

THERMOPLASTIC ELASTOMERS HAVING ENHANCED FOAMING AND PHYSICAL PROPERTIES

BACKGROUND OF THE INVENTION

Field of the Invention

5 This invention relates generally to thermoplastic elastomer (TPE) materials. Thermoplastic elastomers are broadly defined as rubber-like materials that, unlike conventional vulcanized rubbers, can be processed and recycled like thermoplastic materials, yet have properties and performance similar to that of vulcanized rubber at service temperatures. The invention more specifically relates to thermoplastic
10 vulcanizates (TPV), which are thermoplastic elastomers with a cross-linked rubbery phase produced by the process of dynamic vulcanization. The thermoplastic vulcanizates of the invention are foamed materials produced by physical or chemical blowing agents, wherein processing characteristics and foam properties are improved by the inclusion of a modifier derived from polytetrafluoroethylene.
15 The invention also relates to foamed articles obtainable by the process of the invention.

Description of the Prior Art

There has been considerable activity on the development of thermoplastic vulcanizate compositions, especially those based on polyolefin thermoplastic
20 resins, which have good foaming properties, and on processes for producing foams having improved properties. U.S. Pat. No. 5,070,111, incorporated herein by reference, discloses a process of foaming thermoplastic elastomer compositions using water as the sole foaming agent. U.S. Pat. Nos. 5,607,629 and 5,788,889, both incorporated herein by reference, describe methods for the
25 production of foamed thermoplastic elastomer profiles by extrusion with a water blowing agent. U.S. Pat. No. 5,824,400 discloses foamed thermoplastic elastomer

compositions which incorporate styrenic elastomers. Published European Patent Application No. 0 860 465 teaches a method of foaming thermoplastic elastomers using a water containing chemical compound which releases water at temperatures above the melting point of the thermoplastic elastomer. Published
5 European Patent Application 0 872 516 discloses the use of polypropylene resins having specific rheological properties to enhance the foaming performance of olefinic thermoplastic elastomers.

However, the problems of providing thermoplastic elastomer foams which are soft, with good surface smoothness, low water absorption, improved
10 compression set and compression load deflection, and having fine and uniform cell structure have not been overcome by prior art.

SUMMARY OF THE INVENTION

The present invention is based on the discovery that superior thermoplastic elastomer foams can be produced by incorporating into the thermoplastic
15 elastomer, prior to foaming, an acrylic-modified polytetrafluoroethylene. Incorporation of this additive provides a very soft foam product having a number of desirable attributes, including improved processability, high melt strength, high cell density and uniformity, smooth surface, low water absorption, with improved compression set and compression load deflection.

20 In detail the present invention relates to a process for foaming a thermoplastic elastomer using a physical or chemical blowing agent, wherein an acrylic-modified polytetrafluoroethylene is incorporated into the thermoplastic elastomer composition prior to foaming. Sufficient acrylic-modified polytetrafluoroethylene is incorporated to be effective in achieving the desired
25 attributes. The invention also encompasses thermoplastic elastomer compositions containing the acrylic-modified polytetrafluoroethylene, and foamed articles prepared therefrom.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

THERMOPLASTIC ELASTOMER

Thermoplastic Resin Component

Thermoplastic resins suitable for use in the compositions of the invention include thermoplastic, crystalline polyolefin homopolymers and copolymers. They are desirably prepared from monoolefin monomers having 2 to 7 carbon atoms, such as ethylene, propylene, 1-butene, isobutylene, 1-pentene, 1-hexene, 1-octene, 3-methyl-1-pentene, 4-methyl-1-pentene, 5-methyl-1-hexene, mixtures thereof and copolymers thereof with (meth)acrylates and/or vinyl acetates. Preferred, however, are monomers having 3 to 6 carbon atoms, with propylene being most preferred. As used in the specification and claims the term polypropylene includes homopolymers of propylene as well as reactor and/or random copolymers of propylene which can contain about 1 to about 30 weight percent of ethylene and/or an alpha-olefin comonomer of 4 to 16 carbon atoms, and mixtures thereof. The polypropylene can have different types of molecular structure such as isotactic or syndiotactic, and different degrees of crystallinity including materials with a high percentage of amorphous structure such as the "elastic" polypropylenes. Further polyolefins which can be used in the invention are high, low, linear-low and very low density polyethylenes, and copolymers of ethylene with (meth)acrylates and/or vinyl acetates.

The polyolefins mentioned above can be made using conventional Ziegler/Natta catalyst systems or by single site catalyst systems. Commercially available polyolefins may be used in the practice of the invention.

The amount of thermoplastic polyolefin resin found to provide useful thermoplastic elastomer compositions is generally from about 8 to about 90 weight

percent. Preferably, the thermoplastic polyolefin content will range from about 9 to about 60 percent by weight.

Elastomer Component

5 Suitable rubbers include non-polar, rubbery copolymers of two or more alpha-monoolefins, preferably copolymerized with at least one polyene, usually a diene. Saturated monoolefin copolymer rubber, for example ethylene-propylene copolymer rubber (EPM) can be used. However, unsaturated monoolefin rubber such as EPDM rubber is more suitable. EPDM is a terpolymer of ethylene,
10 propylene and a non-conjugated diene. Satisfactory non-conjugated dienes include 5-ethylidene-2-norbornene (ENB); 1,4-hexadiene; 5-methylene-2-norbornene (MNB); 1,6-octadiene; 5-methyl-1,4-hexadiene; 3,7-dimethyl-1,6-octadiene; 1,3-cyclopentadiene; 1,4-cyclohexadiene; dicyclopentadiene (DCPD); and vinyl norbornene (VNB).

15 Butyl rubbers are also useful in the thermoplastic elastomer compositions. As used in the specification and claims, the term butyl rubber includes copolymers of an isoolefin and a conjugated monoolefin, terpolymers of an isoolefin with or without a conjugated monoolefin, divinyl aromatic monomers and the halogenated derivatives of such copolymers and terpolymers. Another suitable copolymer
20 within the scope of the olefin rubber of the present invention is a copolymer of a C₄₋₇ isomonoolefin and a para-alkylstyrene, and preferably a halogenated derivative thereof. The amount of halogen in the copolymer, predominantly in the para-alkylstyrene, is from about 0.1 to about 10 weight percent. A preferred example is the brominated copolymer of isobutylene and para-methylstyrene.
25 Natural rubbers are also olefin rubbers suitable for use in the thermoplastic elastomer composition.

The amount of rubber in the thermoplastic elastomer generally ranges from about 92 to about 10 weight percent. Preferably the olefin rubber content will be in the range of from about 40 to about 91 weight percent.

Additives

5 The thermoplastic elastomer may optionally contain reinforcing and non-reinforcing fillers, plasticizers, antioxidants, stabilizers, rubber processing oils, extender oils, lubricants, antiblocking agents, antistatic agents, waxes, foaming agents, pigments, flame retardants and other processing aids known in the rubber compounding art. Such additives may comprise up to about 70 weight percent,
10 more preferably up to about 65 weight percent, of the total composition. Fillers and extenders which can be utilized include conventional inorganics such as calcium carbonate, clays, silica, talc, titanium dioxide, carbon black and the like. The rubber processing oils generally are paraffinic, naphthenic or aromatic oils derived from petroleum fractions. The oils are selected from those ordinarily used
15 in conjunction with the specific rubber or rubber component present in the composition.

In one particularly preferred embodiment of the invention, the inclusion of an adsorptive inorganic additive has been found to improve the odor properties of the foamed products. The addition of an additive such as magnesium oxide in the
20 range of about 0.1 to about 3 weight percent, preferably about 0.5 to about 2 weight percent, based on the total composition, is effective in eliminating odors.

Processing

The rubber component of the thermoplastic elastomer is generally present as small, i.e. micro size, particles within a continuous thermoplastic resin matrix,
25 although a co-continuous morphology or a phase inversion is also possible depending upon the amount of rubber relative to thermoplastic resin and the degree of vulcanization, if any, of the rubber. Preferably, the rubber is at least partially vulcanized, and most preferably it is fully vulcanized (crosslinked).

The partial or full crosslinking can be achieved by adding an appropriate rubber curative to the blend of thermoplastic olefin polymer and olefin rubber, and vulcanizing the rubber to the desired degree under vulcanizing conditions. It is preferred that the rubber be crosslinked by the process of dynamic vulcanization.

5 As used in the specification and claims, the term dynamic vulcanization means a vulcanization or crosslinking (curing) process wherein the rubber is vulcanized under conditions of shear at a temperature above the melting point of the polyolefin component.

Those of ordinary skill in the art will appreciate the appropriate quantities
10 and types of vulcanizing agents, and the conditions required to achieve the desired vulcanization. Any known crosslinking system can be used, so long as it is suitable under the vulcanization conditions for the elastomer component and it is compatible with the thermoplastic olefin polymer component of the composition. Crosslinking (curing) agents include sulfur, sulfur donors, metal oxides, phenolic
15 resin systems, maleimides, peroxide based systems, hydrosilylation systems, high energy radiation and the like, both with and without accelerators and co-agents.

The terms fully vulcanized or completely vulcanized as used herein mean that the olefin rubber component of the composition has been crosslinked to a state in which the elastomeric properties of the crosslinked rubber are similar to
20 those of the rubber in its conventional vulcanized state, apart from the thermoplastic elastomer composition. The degree of crosslinking (or cure) of the rubber can also be expressed in terms of gel content, crosslink density or amount of uncrosslinked rubber which is extractable by a rubber solvent. All of these descriptions are well known in the art. A typical partially crosslinked composition
25 will have less than about 50 to less than about 15 weight percent of the elastomer extractable by a rubber solvent, while a fully crosslinked composition will have less than about 5 weight percent, and preferably less than about 3 weight percent, of the elastomer extractable by a rubber solvent.

Usually about 5 to about 20 parts by weight of the crosslinking agent or system are used per 100 parts by weight of the rubber component to be vulcanized.

As used herein, the terms thermoplastic elastomer and thermoplastic vulcanizate refer to blends of polyolefinic thermoplastic resin and vulcanized [cured; cross-linked] rubber [elastomer]. Such materials have the characteristic of elasticity, i.e. they are capable of recovering from large deformations quickly and forcibly. One measure of this rubbery behavior is that the material will retract to less than 1.5 times its original length within one minute, after being stretched at room temperature to twice its original length and held for one minute before release (ASTM D1566). Another measure is found in ASTM D412, for the determination of tensile set. The materials are also characterized by high elastic recovery, which refers to the proportion of recovery after deformation and may be quantified as percent recovery after compression. A perfectly elastic material has a recovery of 100% while a perfectly plastic material has no elastic recovery. Yet another measure is found in ASTM D395, for the determination of compression set.

MODIFIED POLYTETRAFLUOROETHYLENE

The composition of the invention includes an acrylic-modified polytetrafluoroethylene (PTFE) component. This component is generally described as a mixture of a polytetrafluoroethylene and alkyl (meth)acrylate having from 5 to 30 carbon atoms. One such blend which is particularly suited for use in the process of the invention is available as Metablen™ A-3000, available from Mitsubishi Rayon Co., Ltd.

The amount of the modified polytetrafluoroethylene component in the composition of the invention generally ranges from about 0.1 to about 4 weight percent, based on the total weight of the composition including the thermoplastic resin component, the rubber component, additives and the modified

polytetrafluoroethylene component. The preferred amount of modified polytetrafluoroethylene ranges from about 0.5 to about 2 weight percent, with about 1 to about 2 weight percent being most preferred. Alternatively, the amount of acrylic-modified polytetrafluoroethylene can be expressed in terms of the total weight of thermoplastic resin and modified polytetrafluoroethylene. The preferred amount of modified polytetrafluoroethylene, expressed in this manner, ranges from about 8 to about 30 weight percent with a range of about 15 to about 30 weight percent being most preferred.

In the preparation of thermoplastic elastomers of the invention, the acrylic-modified polytetrafluoroethylene was generally incorporated directly into the thermoplastic elastomer during production of the thermoplastic elastomer so that it was an integral part of the composition. Alternatively, the acrylic-modified polytetrafluoroethylene can be mechanically blended with a preformed thermoplastic elastomer composition, or it can be introduced into the foaming process simultaneously with the thermoplastic elastomer.

EXAMPLES

The combined thermoplastic elastomer and acrylic-modified polytetrafluoroethylene was fed into an extruder or other mixing device capable of maintaining melt temperatures in the range of about 165°C to about 220°C. If the blowing agent was a solid material, it was also blended with the thermoplastic elastomer prior to introduction into the mixing device. When the blowing agent was a gas or liquid, it was injected into the mixing device through an appropriate inlet. The blowing agent was thus thoroughly dispersed in the molten thermoplastic elastomer, and the mixture was maintained at a pressure sufficient to prevent premature foaming. The mixture was passed through a die or other appropriate outlet, where foaming occurred. The foamed product was cooled in air or in a water mist.

In the following examples thermoplastic elastomers were prepared from blends of polypropylene thermoplastic resin and EPDM rubber, with common

additives and processing aids. Acrylic-modified polytetrafluoroethylene was incorporated into the blends and the rubber component was cross-linked by dynamic vulcanization using a phenolic resin cure system. For the fabrication of foamed articles by an extrusion process, the thermoplastic elastomer was introduced into a single screw extruder and thoroughly melted. The blowing agent, water in the examples set forth in Table 1, was then injected under pressure into the molten thermoplastic elastomer at rates of 1.1 to 1.4 weight percent. The melt was mixed and conveyed, under pressure, to the extruder exit and through a shaping die. The hot and fragile foam was transferred to a conveyor belt where it was cooled by air and water mist. The foamed article may then be cut or shaped for specific applications. Foamed profiles can be either extruded alone as described or coextruded with a dense carrier.

The following measurement methods were used in evaluating the examples of the invention:

15 Tensile strength at break; tensile set; tensile modulus; elongation at break - ASTM D412 (ISO 37, type 2)

Shore hardness - ASTM D2240

Specific gravity - ASTM D792

Surface (Ra) - Surface finish was evaluated as the arithmetic average of roughness irregularities measured from a mean line with the sampling length, using a Surface Analyzer System from Federal Products Corporation, Providence, RI.

Compression set - The sample was compressed inside spaced sample holders to 40% of its initial height, and held at 100°C for 22 hours. The sample was removed and allowed to recover for 30 minutes at room temperature.

Compression set was then determined as: $CS(\%) = (H_{\text{initial}} - H_{\text{final}}) / (H_{\text{initial}} - H_0) \times 100$, where H_0 is the gap of the sample holder (60% of H_{initial}).

Compression load deflection - The force necessary to compress a 100 mm sample to 40% of its original height, at room temperature.

Water absorption - Two test methods were used to measure water absorption. In the first method (A) a weighed foam profile 50 mm long was submerged in water at room temperature two inches below the surface of the water. The specimen was allowed to remain submerged for either 24 hours at atmospheric pressure, or for three minutes at 23 inches Hg vacuum (above the surface of the water). After the appropriate time, the specimen was removed, blotted dry, weighed and the percent change in mass was calculated. In the second method (B) a weighed foam profile 254 mm long was submerged in water at room temperature eight inches below the surface of the water, with a one inch section of the specimen located above the water at each end. The specimen was allowed to remain thus submerged for either 24 hours at atmospheric pressure, or for five minutes at 26 inches Hg vacuum (above the surface of the water). After the appropriate time, the specimen was removed, dried, weighed and the percent change in mass was calculated.

15

TABLE 1

Example ⇒	Con. A	Con. B	1	2	3	4
<u>Components</u> ↓ (parts by weight)						
Polypropylene	42	32	32	32	28	32
EPDM rubber	100	100	100	100	100	100
Process oil	150	150	150	150	150	150
Additives/Curative	63	63	63	63	63	63
Metablen™ A3000	0	0	3	7	7	7
<u>TPE Properties</u> ↓						
Hardness (Shore A)	66	62	61	61	54	57
Ultimate tensile strength (MPa)	6.9	5.3	5.2	4.7	4.2	4.4
Modulus - 100 (MPa)	2.71	1.94	2	1.7	1.5	1.63
Ultimate elongation (%)	520	368	330	317	389	382
Tensile set (%)		8	9	10	8.5	9
Viscosity (poise)	353	544	603	672	707	729
<u>Foam Properties</u> ↓						

Specific gravity (1.1 wt % water)		0.47	0.45	0.47	0.51	0.55
Specific gravity (1.4 wt% water)	0.45	0.4	0.4	0.42	0.45	0.49
Surface (microns)	9.1	8.1	7.8	6.3	8	7.4
H ₂ O absorption (test A) -Atmosphere (%)	38	6.1	2.4	4.8	4.8	2.8
H ₂ O absorption (test A) -Vacuum (%)	50	16.4	14.4	2.8	4.5	3.4
Compression set (%)	52	30	33	31	44	44
Compression load deflection (kg)	0.77	0.6	0.51	0.56	0.31	0.5

As can be seen from the examples, the foamed thermoplastic elastomer of the invention provides a smooth surface, low water absorption,⁵ good compression set and improved compression load deflection. Visual inspection shows that foam cell density is high and the cells are uniform in structure with cell size distribution in a narrow range. Microscopy indicates that about 60% of the cells have a diameter of less than 100 microns.

Additional examples were prepared using different thermoplastic elastomer formulations, and foams were generated using various levels of water as the blowing agent. The foam properties were evaluated, and the results are set forth in Tables 2 and 3.

TABLE 2

Example⇒	5	6	7
<u>Components↓ (weight %)</u>			
EPDM rubber	49.7	49.3	49
Polypropylene	9.1	9	9
Process oil	21.3	21.1	21
Clay	11.9	11.8	11.8
ZnO	0.6	0.6	0.6
SnCl ₂	0.4	0.3	0.3
Curative	1.1	1.1	1.1
Carbon black	4	3.9	3.9
Modified PTFE	2	2	2
MgO	0	0.8	1.4

<u>TPE Properties</u> ↓			
Hardness (Shore A)	60	60	60
Ultimate tensile strength (MPa)	6.3	5.1	3.9
Modulus - 100 (MPa)	2	1.8	1.7
Ultimate elongation (%)	390	470	510
Viscosity (poise)	375	685	485

TABLE 3

Example⇒	5			6			7		
Blowing agent (wt %)	0.9	1.3	1.8	0.9	1.3	1.8	0.9	1.3	1.8
Density	0.59	0.47	0.42	0.55	0.43	0.34	0.6	0.46	0.37
Surface (microns)	6.6	8.1	11.6	5.7	5.2	5.6	5.1	5.4	6.5
H ₂ O absorption (test B) - Atmosphere (%)	0.8	1.7	1.8	0.5	0.7	0.5	0.3	0.5	0.8
H ₂ O absorption (test B) - Vacuum (%)	0.15	0.16	0.18	0.5	0.1	0.1	1	1.5	2.7
Compression set (%)	31	27	27	41	42	40	47	55	63
Compression load deflection (%)	2.1	1.9	1.8	1	0.8	0.6	1	0.6	0.6

5 The materials used in the thermoplastic elastomers of Table 2 were EPDM rubber - Vistalon™ 3666 (ExxonMobil Chemical Co.); polypropylene - D008M™ (Aristech Chemical Corp.); process oil - Sunpar™ 150M; clay - Icecap K™ (Burgess); curative - SP-1045™ (Schenectady International); carbon black - Ampacet 49974 (Ampacet Corp.); modified PTFE - Metablen™ A3000 (Mitsubishi Rayon Co., Ltd.).

The foamed thermoplastic elastomer composition and the molded and shaped articles made therefrom are useful in a variety of applications such as handles and grips for tools or utensils, as well as weather strip for automotive and construction uses.

WHAT IS CLAIMED IS:

1. A thermoplastic elastomer composition comprising
 - A) polyolefin thermoplastic resin,
 - B) olefinic elastomer which is at least partially cured,
 - 5 C) an acrylic-modified polytetrafluoroethylene polymer, and
 - D) optional additives.
2. The composition of claim 1 wherein said acrylic-modified polytetrafluoroethylene polymer is present in the range of about 0.1 to about 4 weight percent, based on the total composition.
- 10 3. The composition of claim 1 wherein said acrylic-modified polytetrafluoroethylene polymer comprises polytetrafluoroethylene which has been modified with an alkyl (meth)acrylate having from 5 to 30 carbon atoms.
4. The composition of claim 1 wherein said polyolefin thermoplastic resin is present in the range of about 8 to about 90 weight percent, and said olefinic
15 elastomer is present in the range of about 92 to about 10 weight percent, based on the total composition.
5. The composition of claim 1 wherein said polyolefin thermoplastic resin is selected from the group consisting of polyethylene, polypropylene and mixtures thereof.
- 20 6. The composition of claim 1 wherein said olefinic elastomer is selected from the group consisting of ethylene-propylene copolymer rubber, ethylene-propylene-diene terpolymer rubber, and mixtures thereof.

7. The composition of claim 1 wherein said olefinic elastomer has been dynamically vulcanized so that less than 15 weight percent of the elastomer is extractable.
8. The composition of claim 1 further comprising a blowing agent.
- 5 9. The composition of claim 8 wherein said blowing agent is selected from the group consisting of water, steam, a water-generating material, or mixtures thereof.
10. The composition of claim 1 wherein one of the additives is magnesium oxide.
11. The composition of claim 10 wherein said magnesium oxide is present in the range of about 0.1 to about 3 weight percent, based on the total composition.
- 10 12. A foam produced from the composition of claim 1.
13. In the process for foaming an olefinic thermoplastic elastomer using a blowing agent, the improvement comprising incorporating into said thermoplastic elastomer, prior to foaming, an effective amount of an acrylic-modified polytetrafluoroethylene.
- 15 14. The process of claim 13 wherein said acrylic-modified polytetrafluoroethylene is incorporated in the range of from about 0.1 to about 4 weight percent, based on the total weight of the thermoplastic elastomer composition.
15. The process of claim 13 wherein said blowing agent is selected from the group consisting of water, steam, a water-generating material, or mixtures thereof.

16. A foamed article prepared using the process of claim 13.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 01/04924

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08L23/02 C08L23/16 C08J9/00 //(C08L23/16,23:10,27:18,33:06)

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08L C08J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DATABASE WPI Derwent Publications Ltd., London, GB; AN 1999-204655 XP002169153 & JP 11 124478 A (MITSUBISHI RAYON), 11 May 1999 (1999-05-11)	1-16
Y	abstract	1-16
X	& WO 99 10431 A (MITSUBISHI RAYON) 4 March 1999 (1999-03-04) the whole document	1-16
T	----- MITSUBISHI RAYON AMERICA: "plastic modifiers" INTERNET, 'Online! XP002169152 Retrieved from the Internet: <URL:www.mrany.com/plastics_modifiers.htm> 'retrieved on 2001-06-06! page 1 ----- -/--	1-16



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

G document member of the same patent family

Date of the actual completion of the international search

8 June 2001

Date of mailing of the international search report

27/07/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.
Fax: (+31-70) 340-3016

Authorized officer

Schmidt, H

INTERNATIONAL SEARCH REPORT

Int. .ational Application No

PCT/US 01/04924

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 5 635 562 A (MALCOLM COLLIN C) 3 June 1997 (1997-06-03) column 3, line 34-49 column 4, line 17-53 column 5, line 33-49 claims 1-7 -----	1-16
A	DE 196 22 736 A (MITSUBISHI CABLE IND LTD) 12 December 1996 (1996-12-12) page 3, line 44-63; table 2 -----	1-16

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 01/04924

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 11124478 A	11-05-1999	JP 2942888 B CN 1271372 T WO 9910431 A	30-08-1999 25-10-2000 04-03-1999
US 5635562 A	03-06-1997	CA 2171160 A	27-10-1996
DE 19622736 A	12-12-1996	CN 1146607 A JP 9055120 A	02-04-1997 25-02-1997